

Product		<b>NEFACIER 1500</b>
Max. temperature [°C]		1500
Colour		Light grey
Specific weight [kg/dm <sup>3</sup> ]		0,9
Recovery [%]		55
$\lambda$ at 400°C [W/m.°K]		0,12
Loss at 800°C [%]		12
Tensile strength [kg/cm <sup>2</sup> ]	Longitudinal fibres	50
	Transversal fibres	40
Shrinkage [%]	at 1000°C (24 hours)	1,2
	at 1150°C (24 hours)	4,0
Compressibility according to ASTM F36 method K [%]	70kg/cm <sup>2</sup>	7
Thickness [mm]	Tolerance: $\pm 10$ %	5
Dimensions [mm]		1000 x 1000
Composition of the board		Asbestosfree millboard based on ceramic fibres with low content of non-fibrous ceramic particles
Applications		Thermal barrier shields and heaters, dryers, etc.

*The given data is intended for information only. The manufacturer holds no responsibility for failures arising from bad application of the product. Interference with this document are prohibited.*